

TC7UVZ (UV/AP Series)
THERMOLAST® K
Applications requiring high UV resistance
Typical applications

- Roof rims
- Water deflectors
- Window encapsulations

Material advantages

- Adhesion to PP
- Easy flowing
- Excellent mechanical properties
- Excellent UV- and weather resistance

Processing Method: Injection Molding

Product properties
Compound name TC7UVZ

Series UV/AP

Color / RAL DESIGN black

Mechanical properties

Hardness	70 ShoreA	DIN 53505/ISO868
Density	1.190 g/cm ³	DIN EN ISO 1183-1
Tensile Strength ¹	6.2 MPa	DIN 53504/ISO 37
Elongation at Break ¹	600 %	DIN 53504/ISO 37
Tear Resistance	26.0 N/mm	ISO 34-1 Methode B (b)(Graves)
CS 72 h/23 °C	24 %	DIN ISO 815-1 Method A
CS 24 h/70 °C	59 %	DIN ISO 815-1 Method A
CS 24 h/100 °C	74 %	DIN ISO 815-1 Method A

¹ Deviating from ISO 37 standard test piece S2 is tested with a traverse speed of 200 mm/min.

ASTM test results according to GMW16233 specification upon request by customer.

All values published in this data sheet are rounded average values.

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.

2019-01-22


CUSTOM-ENGINEERED TPE AND MORE

© 2019 by KRAIBURG TPE
Subject to change, errors excepted.
Check www.kraiburg-tpe.com for the latest version

TC7UVZ (UV/AP Series)
THERMOLAST® K
Compression Set
Compression Set (acc. DIN ISO 815)

For the compression set testing the following specimen is used:

The specimen is a cylindrical disk shaped 6 mm thick and 13 mm in diameter.



The specimen is compressed by 25%. The compressed specimen is heated to the test temperature. DIN ISO 815 describes two methods.

Method A: The specimen is allowed to recover immediately after its aging in the oven and then cooled down to room temperature. After 30 minutes the thickness of the specimen is measured and the compression set calculated.

Method B: The specimen is cooled down to room temperature after its aging in the oven and then allowed to recover.

Test results gained from method B are in general higher than from method A.

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.

TC7UVZ (UV/AP Series)
THERMOLAST® K
Processing Guideline Injection Molding

Cylinder temperature	180 - 200 - 220 °C, max. 250 °C (360 - 390 - 430 °F, max. 480 °F)
Hotrunner	Hot runner temperatures: 200 -250 °C (390 - 480 °F). The runner should be empty after a maximum of 2 - 3 shots.
Injection pressure	200 - 1000 bar (2900 - 14504 psi) (depending on the size and weight of the part).
Injection rate	In general, the fill time should not be more than 1–2 seconds.
Hold pressure	We recommend to derive the optimum hold pressure from determining the solidification point, starting with 40 % - 60 % of the required injection pressure.
Back pressure	20 - 100 bar; if color batches are used, higher back pressure is necessary.
Screw retraction	If an open nozzle is used processing with screw retraction is advisable.
Mold temperature	25 - 40 °C (77 - 104 °F)
Predrying	Pre drying of the material is not necessary; if surface moisture forms as a result of changes in temperature, the material should be dried for 2 - 4 hours at 60 - 80 °C (140 - 175 °F).
Needle valve	With materials < 50 Shore A the use of a needle valve is advisable.
Screw geometry	Standard 3-zone polyolefine screw.
Residence time	The residence time is to be set as short as possible with a maximum of 10 minutes.
Cleaning recommendation	For cleaning and purging of the machine it is appropriate to use polypropylene or polyethylene. Machine must be PVC-free.

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.

2019-01-22

CUSTOM-ENGINEERED TPE AND MORE

© 2019 by KRAIBURG TPE
Subject to change, errors excepted.
Check www.kraiburg-tpe.com for the latest version